

## **Technical Data Sheet**

# **Release Film** HCS2108-NP HCS2108-P

#### **Product Description**

HCS2108-NP and HCS2108-P is an FEP resin base release film. HCS2108-NP and HCS2108-P exhibits high elongation and excellent release characteristics. It follows all complicated shape of parts without bridging. Suitable for use with all commonly used resin systems up to 500°F (260°C). Color deep red makes it easily detectable on cured laminate. This release film is supplied in both perforated and non-perforated versions.

#### **Properties**

Material	FEP
Maximum Use Temperature	500°F (260°C)
Color	Red
Tensile Strength	MD: 23MPa
	TD: 15MPa
Elongation	MD: 160%
	TD: 200%
Density	25µm (43g/m²)

## **Availability and Packaging**

Thickness	25µm, 51µm (0.001", 0.002")
Width	1.22m, 1.27m, 1.52m (4.0', 4.2', 5.0')

### Storage

Store in its original packaging.

#### **Notes**

No skin irritation problems experienced and no other special requirement.

**CORPORATE HEADQUARTERS** 480 Andover Park East Seattle, WA 98188 P: (206) 575-1333 F: (206) 575-0856

info@heatcon.com www.heatcon.com

